REPORT OF CONCRETE CYLINDER TEST

MAPPA TESTLAB
1956 Richardson Hwy, North Pole, AK

Report Date: 6/30/26

Project Number: Red Point DTA017 26 Report Number: 1
Project: DTA017 Donnelly Training
Client: Red Point Construction
Address:

Attn:


FIELD TEST CONDITIONS AND RESULTS (ASTM C 31)

Date Placed: 6/2/2026
Time Sampled: 230pm
Location of Sample: Texas Cando Tank Pad
Supplier: URM
Truck Number: Ticket Number: 9108
Mix Number: D3450I
Design Strength: 5000
Batch Size:
Slump: 5.50" (ASTM C 143) Air Content: 4.4% (ASTM C 231) Unit Weight: 147.96 (ASTM C 138)
Concrete Temp: 56°F (ASTM C 1064) Ambient Temp: 71°F
Water Added: Technician: Ben Marth
Initial Curing: Final Curing:
Max Field Curing Temp.: Min Field Curing Temp.:

LABORATORY TEST RESULTS (ASTM C 39)

Specimen	Test Date	Age	Load	Diameter	Area	Strength	Percent of Design	Type of Fracture
26-575	6/9/2026	7	57655	4.00	12.57	4590	92%	3
26-576	6/9/2026	7	59300	4.00	12.57	4720	94%	3
26-577	6/16/2026	14	65620	4.00	12.57	5220	104%	2
26-578	6/30/2026	28	72030	4.00	12.57	5730	115%	3
26-579	6/30/2026	28	71755	4.00	12.57	5710	114%	3

Remarks:



Copies to:

Reported by:
Chris Mack, C.E.T.
Concrete Lab Supervisor